DEPARTMENT OF TRANSPORTATION STATE OF GEORGIA

INTERDEPARTMENT CORRESPONDENCE

JAN 1 8 2013

OFFICE OF

FILE:

0010925 Fulton

Riverside Drive / I-285

PI NO. 0010925

OFFICE: Materials

Forest Park, Georgia

DATE: January 18, 2013

FROM:

Charles A. Hasty, P.E., State Materials Engineer

TO:

Marlo L. Clowers, P.E., Project Manager, Office of Innovative Program Delivery

RE:

Bridge Deck Condition Survey

As requested, this office has completed the bridge deck condition survey on the above reference project. This 4 span bridge deck was evaluated for concrete quality and depth of reinforcement.

The steel cover on this bridge deck averaged 1.35 inches with a range of less than 1 inch to 1.9 inches. Visual inspection of the deck revealed moderate surface wear with exposed aggregates, the worst in Span 2. Moderate transverse cracking occurs in all spans about every 3 foot with some as close as 1 foot apart. In Spans 2 and 3 there are spalls with exposed corroded reinforcement bars. Map cracking was also found in all spans. Delamination was found in Spans 2 and 3. Cores were obtained and those with reinforcement indicated signs of corrosion in both of the top and bottom reinforcement bars. The strength cores yielded an average compressive strength of 4251 psi. Chloride samples taken from the deck indicated a chloride density of 2.91 lbs./yd³ at the 1 inch depth, and 2.87 lbs./yd³ at a 2 inch depth. Corrosiveness can occur when chloride is over 2 lbs./yd³ within the concrete. The deck thickness is 6.38 inches and the bridge was built in 1962.

Visual inspection of the underside of the deck revealed transverse cracking with effervescent was in all spans. The cap at Bent 2 and 3 has spalling with vertical exposed rebar. The remaining substructure appears to be in sound condition at this time.

Based on these findings, it is recommended that the bridge deck be removed and replaced with a new concrete deck as specified in Section 500 – Concrete Structures. Also the spalls in the caps at Bent 2 and 3 should be repaired during construction. If you have further questions concerning these surveys, please contact James Page of this office at 404-608-4876.

CAH: JMP: jkd

Attachments

Dulworth, Jeff

From:

Page, James

Sent:

Monday, December 10, 2012 5:41 PM

To:

Dulworth, Jeff

Subject:

FW: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition

Survey

See when you can get traffic control set up for this. Thanks

From: Clowers, Mario

Sent: Monday, December 10, 2012 11:58 AM

To: Hasty, Charles A. (Chuck) **Cc:** Page, James; Wu, Peter

Subject: RE: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Thanks Chuck.

From: Hasty, Charles A. (Chuck)

Sent: Monday, December 10, 2012 11:48 AM

To: Clowers, Marlo

Cc: Page, James; Wu, Peter

Subject: RE: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Marlo:

Myron Banks retired May 31, 2012. I am forwarding your request to Mr. James (Jay) Page, Concrete Branch Chief for further action.

Charles A. (Chuck) Hasty, P.E., M.S.C.E. State Materials Engineer Georgia Department of Transportation 15 Kennedy Drive Forest Park, Georgia 30297

Voice (404) 608-4708 Facsimile (404) 608-4752 Mobile (404) 895-5004

From: Clowers, Marlo

Sent: Monday, December 10, 2012 11:32 AM

To: Hasty, Charles A. (Chuck)

Subject: FW: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Chuck,

I sent the request below to Myron Banks this morning and it came back marked undeliverable. Could you please forward this to the person handling bridge deck condition surveys now? Let me know if you have any questions. Thanks

Ms. Marlo L. Clowers, P.E. Project Manager Office of Innovative Program Delivery

Georgia Department of Transportation One Georgia Center, Suite 1900 600 West Peachtree Street, NW Atlanta, Georgia 30308 404.631.1713 mclowers@dot.ga.gov

From: Clowers, Marlo


Sent: Monday, December 10, 2012 11:24 AM

To: 'Banks, Myron'

Subject: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Myron,

This email is to request a bridge deck condition survey for the above listed design-build project, which is expected to be let in August 2013. The bridge structure ID number is 121-0452-0. It is a bridge on CR 209/Riverside Drive over I-285. A location sketch is below. If you have any questions please contact Marlo Clowers at mclowers@dot.ga.gov or 404.631.1713. Thank you



Ms. Marlo L. Clowers, P.E. Project Manager Office of Innovative Program Delivery

Georgia Department of Transportation One Georgia Center, Suite 1900 600 West Peachtree Street, NW Atlanta, Georgia 30308 404.631.1713 mclowers@dot.ga.gov

During inclement winter weather, Georgia DOT's priority is to clear travel lanes on the state's most-used roadways – the Interstate Highway System and other major arterial roads. The Department urges travelers to exercise caution and call 511 for updated information on roadway conditions before getting on the road during a winter weather event.

Visit us at http://www.dot.ga.gov/winterweather; or follow us on http://www.facebook.com/GeorgiaDOT and http://twitter.com/gadeptoftrans

Parameters: Bridge Serial Num

Processed Date:12/11/2012





Structure ID:121-0452-0		Fulton		SUFF. RATING: 76.40		
Location & Geography			•	Signs & Attachments		
Structure ID:	121-0452-0	"104 Highway System:				
		*26 Functional Classification:	17	225 Expansion Joint Type:	83	
200 Bruge imprination:		*204 Federal Route Type:	M No; 09248	242 Deck Drains:	0	
*6A Feature Int *6B Critical Bridge:	1-285 (SR 407)	105 Federal Lands Highway:	0	243 Parapet Location:	0	
	0	*110 Truck Route:		to de la companya de	c	
A NOW HO CAMED.	200000	2006 School Bus Route:			,	
-7B Facility Carried:	RIVERSIDE DRIVE	217 Benchmark Elevation	00 0000	With:	0	
Location:	IN N FULTON			238 Curb Height:	-	
Dot District:	7	218 Datum:	o o	Curb Meterial:	-	
		#10 Demans Langeth	5	239 Harbari	;	
207 Year Photo:	2011	15 syptem cangar		10 Maria 1007	= ,	
	24 024000011	*20 Toll:	m	7240 Medium Barrier Rait	0	
91 illapedion Frequency. 92A Food Cot loss Fred	8	*21 Maintanance:	2	241 Bridge Median Height	•	
+	Care	*22 Owner:	10	• Bridge Median Width:	0	
92B Underwater Insp Freq:	0 Date: 02/01/1901	*31 Design Load:	9	230 Guardrall Loc. Dir, Rear.	60	
92C Other Spc. Insp Freq:	0 Date: 02/01/1901	17 Historical Significance:	vo.	Fwrd	es	
* 4 Place Code:	68516	206 Commissed District	8	Oras Dir Rest		
*5 Inventory Route(O/U):	-	203 Confressiona District	3		, (
	u*	27 Year Constructed:	1962	Oppo, Fwrd:	0	
Type:	1 ,	106 Year Reconstructed:	0000	244 Aproach Slab	en	
Designation:	-	33 Bridge Medium:	0	224 Retaining Wall:	0	
Number.	09248	34 Skew:	00	233Posted Speed Limit	36	
Direction:	0	35 Structure Flared:	0	238 Warning Sign:	0.00	
*16 Latitude:	33 54.954 HMMS Prefix	20 Manipustice Control.	Z	234 Delineator	80	
*17 Longritude:	84 -24.3995 HMMS Suffix MP:0.00		: e	The state of the s	•	
98 Border Bridge:	000%Shared:00	713 Special Steel Lieugn.			. 8	
in the second se	COCCOCCOCCOCC	267 Type of Paint:	ın.	237 Utilities Gest	23	
99 ID Number:	o consesso con con	*42 Type of Service On:	ın	Water:	8	
*100 STRAHNET:	5	Type of Service Under.	-		8	
12 Base Highway Network:		214 Movable Bridge:	0		3 ;	
13A LRS inventory Route:	1212020900	203 Tyne Bridge	2	i alephone;	7	
13B Sub Inventory Route:	0	of City Engagement	l 67	Sewer	8	
101 parellel Structure:	z	COST NG CINCOGIII CIT		Contract Charles	ć	
0103 Direction of Touffier	•	43 Structure Type Main:	70 e	The Principle States	,	
A Director of Limits.	26 36	45 No.Spans Main:	900	Nevigation:	0	
264 Road Inventory Mile Post:	onding	44 Structure Type Appr.	00 0			
208 Inspection Area:	. 7 Initials; EFP	48 No Spans Appr.	0000	10 mg	٠ ;	
Engineer's Initials: Location ID No:	121-09248M-000,60N	228 Bridge Curve Horz	0 Vert 1	748 County Continuity No.:	3	
		111 pier Protection	0			
		107 Deck Structure Type:	-	14		
// !		108 Wearing Structure Type:	,			
1000/101/	/w/		•			

steel bams

Membrane Type: Deck Protection:

File Location: CF Conversions/BIMS
The Information contained in this File/Report is the property of GDOT and may not be released to any other party without the written consent of the Data Custodian. Please dispose of this information by shredding or other confidential method."

Bridge Inventory Data Listing



Parameters: Bridge Serial Num

Processed Date:12/11/2012

Structure ID:121-0452-0	52-0				
Programming Data	1-285-1 (16) 88 CT.2	Measurements:	00000 N 0000	65 Inventory Rating Mathod:	2
202 Plans Available:	4	-29AD1	uosseo rearzou/	63 Operating Rating Method;	8
249 Prop Proj No:	IM-285-1(351)	109761 nucks:		86 Inventory Type:	2 Rating: 38
250 Ameroval Status:	0000	* 28 Lanes On:		64 Operating Type:	2 Bating: 36
251 Pl Number.	713230-	210 No. Tracks On:	00 Under:00	231Calculated Loads.	
242 Coursest Date.	02/01/1901	. 48 Max. Span Length	0073	H.Modified.	2000
260 Seismic No:	00000	• 49 Structure Length:	258	Le Moditori	3 C 46
		51 Br. Rwdy. Width	28.00		
75 Type Work:	34 -	52 Deck Width:	40.00	Type 3:	28 D
94 Bridge Imp: Cost:	\$538	• 47 Tot Horiz Ci-	28	Type 3s2:	40 0
95 Roadway Imp. Cost:	88		3	Timber	360
96 Total Imp Cost:	773	50 Curb / Sidewalk Width	5.00 / 5.00	Piggy back:	0 00
76 Imp Length:	-200005	32 Approach Rdwy, Width	028	261 H Inventory Rating:	20
97 Imp Year:	1990	*229 Shoulder Width:		262 H Operating Rating	28
114Furure ADT.	008970 Year.2030	Rear Lt.	2.00 Type:3 Rt2.00	67 Structural Evaluation:	ω
		First Lr.	2.00 Type:1 Rt2.00	58 Deck Confition:	60
Hydralic Data				59 Superstructure Condition:	89
215Waterway Data:		Permanent Width:		* 227 Collision Damage:	o
High Water Elev.	0000,0 Year:1900	Rear	24,00 Type:3	80A Substructure Condition	7
Flood Elev.	0000,0 Freq:00		24.00 Type:2	and owner Conditions	- 2
Avg Streambed Elev.	0000,0	Intersaction Rear.	1 Fwd: 1	SPO Indemoter	
Drainage Area:	00000	38Safety Features Br. Rail:	2	SUC UNGERWARE CONGISON	2 7
Area of Opening:	000000	Transition:	2	1 Water way Autoquary.	z :
113 Scour Critical	Z	App. G. Railt	2	61 Channel Protection Cond.	2
216Water Depth:	00.0 Br.Height 00.0	App. Rail End:	-	oo Least Geometry.	4 (
222Slope Protection:	4	53 Minimum Cl. Over.	66. 56	as Under Lift, Florziver.	7 (
221Slope Protection	0.00%	Under		72 Appr. Alignment	
2) O'Conder System	a	*228 Minimum Vertical Cl		62 Culvert:	z
220Dolphin.	0	Act. Odm Dir:	.88, 88,	Postding Data	
223Curent Cover.	000	Oppo. Dir.	.66, 88,	70 Bridge Posting Required	ın
Type		Posted Odm. Dir.	00.00	41 Struct Open, Posted, CL:	⋖
No. Barrels:	0	Oppo, Dir.	00.00	 103 Temporary Structure: 	0
• Width:	0.00 Height 0.00	55 Lateral Underd. Rt.	H22	232 Posted Loads	
• Length:	0 Apron:0	56 Lateral Underd, Lt.	5.00	H-Modified:	00
265 U/W Insp. Area	0 Diver2222	*10 Max Min Vert CI:	99° 99" Dir.0	HS-Modified:	00
Location ID No:	121-09248M-000.60N	39 Nav Vert Ct:	000 Horiz:0000	Type 3:	00
		116 Nav Vert Cl Closed:	000	Type 3s2:	00
		245 Deck Thickness Main	7.50	Timber	00
		Deck Thick Approach:	0,00	Piggyback	8
		248 Overlay Thickness:	Z, DO	253 Notification Date:	02/01/1901
		212 Year Last Painted:	Sup;1995Sub;0000	258 Fed Nothly Date:	2/1/1901 12:00:00AA

File Location: CF Conversions/BIMS

The Information contained in this File/Report is the property of GDOT and may not be released to any other party without the written consent of the Data Custodian, Please dispose of this Information by stredding or other confidential method,"

rpe De	ck Forms		Project Er	ng.				
,,				Jeff Dulwo			·	
ane	width	lane	width	lane	width	lane	width	1 .
	,							Bent #5
10	10	10	10	10	10	10	10	
9	9	9	9	9	9	9	9	2 1 1 1
3 .	. 8	8	8	8	8	8	8	
	7	7	6	7	7 6	7	7 6	Span length 4/1
<u> </u>	6	6		6	5	6		Shari lengmi 41
2	5	5	5	5		5 4	5 4	10 1
4	4	4 3	4	4	3 / ->-	B		
9 8 7 6 5 4 3 2	3		37.45	3 1,6	3 40 2000	220	3 34	
<u> </u>	1	2	1 7	1 113	2 1.5	142	134	Bent #4
	10	10	10	10	10	10	10	Dent 7
10 9	9	9	9	9	9	9	9	7
3	8	8	8	8 1.7	8 to Non	1		
7	7	7	7 (7 1.0	7 1.3	7 42	83 <i>S</i> 7 <i>3</i> .5	
3	6	6		61.2	6 17	640	634	Span length
5	5	5 60	16	5 toN	5 1.1	534	54//	
1	4	4	14	4 400	4 1.3		436	
3	3	3	3	4 to Non	3 1.3	3 38	342	
2	2	2	2	2 110	2 1.7	2 38	2.34	
1	1	1	1	1 1,0	1 113	142	2 38	Bent ∄¬¬
10	10	10	10	10	10	10	10	
9	9	9	9	9 116	9	9	9	
3	8	8	8 /	8 1.4	8 1.5	8 42	8 34	
7	7	7	7	7 /A	7114	7 38	8 34 7 34	
6	6	6	6)	6 1,5	61.2	6 4Z 5 38	6 3 %	Span length 1
5	5	5	5	5 1.0	5 /12	5 38	5 3 5	*
4	4	4 1.3	44	4 1.4	4 +2 pm	4 43	3 3 5	
3	3	3/ 1	ß	3 1.6	3/ap	3 42]
2	2	2	2	2 1,7	2 1.4	2 35	2 38	
1	. 1	1	1 6	1 1,4	1 1.5	1 30	1 4/1	Bent # 7_
10	10	10	10	10	10	10	10	
9 8 7	9	9	9	9	9	9	9	
8	8	8	8	8 1,9	8 1. L	8 /	8	_
	7	7	7	7 Q 6 1.3	7 1.8	7 35	7.41	Span length 68
6	6	$\frac{6}{}$	6		6 / 4	6 40 5 40	6 4/	Span length 40
5	5	51,4) 5	5 1.6	5 1.3		5 38	
4	4	4	14)	4 1.6	4 1.1	4 39 3 40	435	-
3	3	3	<u> </u>	3 1.3	3 1.5		3 38	4
4 3 2 1	2	2	12	2 1.0	2 tenue	14 "-4	2 4Z 1 28	
	11	1	177	17 1.5	1 to Now			Bent # 1
N.S.E.V	v. N.S.E.V	N.S.E.W	N.S.E.W.	N.S.E.W.	N.S.E.W.	NSEW	NS.E.W.	
		chiecoll.	1.35 1.35			SH	SH	39.57 -40
		_	1 25	COVE		<i>→ (1</i>	1	37.51 70

5W155 Hamma1

Bridge Deck Survey Drawing per spans Date 12'28-2012 PROJECT NO. DOLD925 Location Riverside DR MSEW 20' App SIMB with Enhant August Valley with (NS EW Corrstaken & Fidenall 2' 11 1 Span length 1.5 48' 2' 6 C/5 2' Bent \$2

165

Bridge Deck Condition Survey

Inspection Date 1 9, 2013

Bridge Location Riverside Drive / I-285

County Fulton

Project No.0010925

Structure No. 121-0452-0

DateBuilt 1962

Widen

MP

Type Structure: Psg

StgXXX Ptbg

Rcdg

Number of Spans: 4 Spam Lengths1.)68', 2.)71', 3.)71', &4.) 41'

Bridge Width 40 ft.

Deck Thickness 7.5 in.

Asphalt Thickness On Bridge Deck if any 0 in.

Steel Cover: Avg1.35 in.

Per / Span1.)1.4 , 2.)1.3 , 3.)1.3 ,4.)1.4

Swiss Hammer: 5500 (psi)

Core Data

Core No.	Deck Thickness	Top Cover	Asphalt Thickness	Strength
1.	6.375"	0.937	0	psi
2.			0	4286 psi
<i>3</i> .			0	3802 psi
<i>4</i> .			0	4664 psi

Visual Inspection: (Cracking, Spalling, Corrosion, Ect.) (By Span, Add Additional Sheets as needed)

Moderate transverse cracking was visual in all spans spacing as close to 1' apart. Moderate surface ware with polished aggregates in all spans with the worst in span 2, map cracking was located in all spans. Spans 2 and 3 have some areas of delamination. Visual inspection of the substructure revealed spalls in the caps at bent 2 and 3 with exposed corroded rebar on the North facing. All spans have full depth transverse cracking with effervescent.

CONCRETE CORE DATA

Report Date: 1/9/2013

Contract ID No.: Project No.: 10925

> County: Fulton District No.: 7

Location: Riverside Drive / I-285

Date Placed: 1/1/1962

Concrete Supplier:

Class Concrete: AA Design Strength (psi): 3500

DOT 319 Card No.:

Cylinder Nos.:

Core ID:		1			2			3	· 数。
Date & Time Cored:	1/9/2013	10:15 AM	18636	1/9/2013	10:20 AM	18636	1/9/2013	11:20 AM	1863
Time Sealed:		10:20 AM	0:05		10:25 AM	0:05		11:30 AM	0:1
Cored Length (in.):	5.000			4.500			5.188		
Core Preparation		-70			302-32-30				
Date & Time Prep'd:	1/9/2013	12:20 PM	0	1/9/2013	12:22 PM	0	1/9/2013	12:23 PM	0
Time Sealed:		12:22 PM	0:02		12:23 PM	0:01		12:25 PM	0:0
End Prep:	Sawn - Wet			Sawn - Wet			Sawn - Wet		
Diameter (in.):	2.780			2.780			2.780		
Area (in²):	6.07			6.07			6.07		
Cut Length (in.):	3.810			4.590			4.020		
Cut L/D Ratio:	1.37			1.65			1.45		
Date & Time Capped:	1/9/2013	1:40 PM	0 -	1/9/2013	1:45 PM	0	1/9/2013	1:43 PM	0
Time Sealed:		1:50 PM	0:10		1:50 PM	0:05		1:50 PM	0:0
Capping Material:	Sulfur			Sulfur			Sulfur		
Capped Length (in.):	4.070			4.850			4.220		
Avg. Cap Thick. (in.):	0.260			0.260			0.200		
Capped L/D Ratio:	1.46			1.74			1.52		
Density		11	1111		arenes - University			11	
Date & Time Tested:	1/9/2013	1:32 PM	18636	1/9/2013	1:34 PM	18636	1/9/2013	1:35 PM	186
Weight (lbs.):	2.000			2.400			2.100		
Volume (in 3):	23.13			27.86			24.40		
Unit Weight (lbs./ft3):	149.4			148.9			148.7		
Compressive	XX 785	A 15			8	10			
Date & Time Tested:	1/9/2013	2:11 PM	18636	1/9/2013	2:00 PM	18636	1/9/2013	2:15 PM	186
Direction of Load:	Parallel			Parallel			Parallel		
Max. Load (lb,):	27,240			23,570			29,460		
Type Fracture:	Columnar			Columnar			Columnar		
Comp. Strength (psi):	4488			3883			4853		
Correction Factor:	0.955			0.979	V////////		0.961		
Adj. Strength (psi):	4286			3802			4664		
Aggr. Size:	57			57			57		
Core Location:	Core obtained from S Bound Lane cored 1: 9' from the West side core has the bottom so corrosion on the r	2.5' from Bent e of the bridge. mat of rebar th	1 and This	Core obtained from Bound Lane cored 1 8.5' form the West s	2.6' from Bent		Core obtained from Bound Lane cored 1 from the West side of core had some of the had some corrosion	0' from Bent 5 of the bridge. ne bottom reba	and 8 This

Compressive Strength (psl)
Average = 4251

Std Dev. = 432

COV = 10.2

Unit Weight (lbs/cu. ft.)

Average = 149.0 Std Dev. = 0.4

COV = 0.3

Remarks: The Steel depth core read too near and measured at .9375" rebar had corrosion.











Georgia Department of Transportation Office of Materials and Research Miscellaneous Sample Report

	Tribedianeous Sumple Report						
Sample Number:	BROO2166-13-008053						
Date Received:	1/9/2013 Project No.: BRIDGE DECK EVALUATION						
County Number:	121 Fulton						
Contract No.:	Sample Type: Technical Services						
Producer Code:	QPMISC Miscellaneious Supplier (Non-QPL) Statewide						
Material Code:	MISCEL Miscellaneous Products						
Date Sampled:	1/9/2013 Sampled From: Bridge						
Quantity:	1 Unit: GRAM						
Location:	Jeff Dulworth, CS-213 Examined For: 884.01						
Vendor:							
Date Completed:	1/11/2013						
Remarks:	Please return results to Jeff Dulworth of the Concrete Section. Producer - GDOT Sample from Bridge Deck Location: I-85 Riverside Drive Concrete Dust @ 2" Depth Corrosiveness can occur over 2lbs/yd3 for Concrete.						
Meets Requiremen	Meets Requirements: Failed Sample Used for Source Evaluation						
Test Data:							
Chloride Content in Chloride% =07% Chloride lbs/yd3 = Corrosiveness can o							
	•						

STATE MATERIALS AND RESEARCH ENGINEER

Georgia Department of Transportation Office of Materials and Research Miscellaneous Sample Report

Sample Number:	BROO2166-13-008054					
Date Received:	1/9/2013 Project No.: BRIDGE DECK EVALUATION					
County Number:	121 Fulton					
Contract No.:	Sample Type: Technical Services					
Producer Code:	QPMISC Miscellaneious Supplier (Non-QPL) Statewide					
Material Code:	MISCEL Miscellaneous Products					
Date Sampled:	1/9/2013 Sampled From: Bridge					
Quantity:	1 Unit: GRAM					
Location:	Jeff Dulworth, CS-113 Examined For: 884.01					
Vendor:						
Date Completed:						
Remarks: Please return results to Jeff Dulworth of the Concrete Section. Producer - GDOT , Sample from Bridge Deck Location: I-85 Riverside Drive Concrete Dust @ 1" Depth Corrosiveness can occur over 2lbs/yd3 for Concrete.						
Meets Requireme	nts: Failed Sample Used for Source Evaluation					
Test Data:						
Chloride Content in Chloride% =07% Chloride lbs/yd3 = Corrosiveness can						
	•					
	· ·					

STATE MATERIALS AND RESEARCH ENGINEER

DEPARTMENT OF TRANSPORTATION

STATE OF GEORGIA OFFICE OF INNOVATIVE PROGRAM DELIVERY 600 WEST PEACHTREE, ST, NW, SUITE 1900 ATLANTA, GEORGIA 30308

LETTER OF TRANSMITTAL

TO: Charles A. Hasty	DATE: December 10, 2012
State Materials Engineer	PROJECT: 0010925
	COUNTY: Fulton
Н.	P.I. NUMBER: 00010925
Attn: James Page	
PROJECT DESCRIPTION	I: I-285 @ CR 209/Riverside Drive
WE ARE SENDING YOU THE FOLLOWING ITEMS:	☑ ATTACHED ☐ UNDER SEPARATE COVER
 □ CORRESPONDENCE □ SPECIAL PROVISIONS □ RIGHT OF WAY PLANS □ CONSTRUCTION PLANS □ PRINTS 	 □ PRELIMINARY PLANS □ REVISION(S) □ PLAN SHEETS □ PROFILE SHEETS □ TYPICAL SECTIONS □ DETAILED ESTIMATE
COPIES	DESCRIPTION
1 Emai	Request for Bridge Deck Condition Survey
1 Locat	ion Sketch
9 1	
	·
THESE ARE TRANSMITTED ☑ AS REQUESTED ☐ FOR REVISION	
REMARKS: If you have telephone at (404) 631-17	any questions, please contact Marlo Clowers by e-mail or 13.
Attachment	SIGNED Claves for STATE INNOVATIVE PROGRAM DELIVERY ENGINEER
	CO 1 2012 M.A

Georgia Department of Anna Control of Anna Con

Clowers, Mario

From:

Page, James

Sent:

Monday, December 10, 2012 12:02 PM

To:

Clowers, Marlo

Cc:

Wu, Peter; Hasty, Charles A. (Chuck)

Subject:

RE: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Marlo,

If you would mail a hard copy of this request to my attention for the file. Once we receive the copy we will get traffic control scheduled and get the process started on this bridge survey.

Thanks

James Page

From: Clowers, Marlo

Sent: Monday, December 10, 2012 11:58 AM

To: Hasty, Charles A. (Chuck) **Cc:** Page, James; Wu, Peter

Subject: RE: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Thanks Chuck.

From: Hasty, Charles A. (Chuck)

Sent: Monday, December 10, 2012 11:48 AM

To: Clowers, Marlo

Cc: Page, James; Wu, Peter

Subject: RE: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Marlo:

Myron Banks retired May 31, 2012. I am forwarding your request to Mr. James (Jay) Page, Concrete Branch Chief for further action.

Charles A. (Chuck) Hasty, P.E., M.S.C.E. State Materials Engineer Georgia Department of Transportation 15 Kennedy Drive Forest Park, Georgia 30297

Voice (404) 608-4708 Facsimile (404) 608-4752 Mobile (404) 895-5004

From: Clowers, Marlo

Sent: Monday, December 10, 2012 11:32 AM

To: Hasty, Charles A. (Chuck)

Subject: FW: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Chuck,

I sent the request below to Myron Banks this morning and it came back marked undeliverable. Could you please forward this to the person handling bridge deck condition surveys now? Let me know if you have any questions. Thanks

Ms. Marlo L. Clowers, P.E.
Project Manager
Office of Innovative Program Delivery

Georgia Department of Transportation One Georgia Center, Suite 1900 600 West Peachtree Street, NW Atlanta, Georgia 30308 404.631.1713 mclowers@dot.ga.gov

From: Clowers, Marlo


Sent: Monday, December 10, 2012 11:24 AM

To: 'Banks, Myron'

Subject: 0010925, Fulton - I-285 @ Riverside Drive Roundabouts - Bridge Deck Condition Survey

Myron,

This email is to request a bridge deck condition survey for the above listed design-build project, which is expected to be let in August 2013. The bridge structure ID number is 121-0452-0. It is a bridge on CR 209/Riverside Drive over I-285. A location sketch is below. If you have any questions please contact Marlo Clowers at mclowers@dot.ga.gov or 404.631.1713. Thank you



Ms. Marlo L. Clowers, P.E. Project Manager Office of Innovative Program Delivery

Georgia Department of Transportation One Georgia Center, Suite 1900 600 West Peachtree Street, NW Atlanta, Georgia 30308 404.631.1713 mclowers@dot.ga.gov

During inclement winter weather, Georgia DOT's priority is to clear travel lanes on the state's most-used roadways – the Interstate Highway System and other major arterial roads. The Department urges travelers to exercise caution and call 511 for updated information on roadway conditions before getting on the road during a winter weather event.

Visit us at http://www.facebook.com/GeorgiaDOT and http://www.facebook.com/GeorgiaDOT and <a href="

